



# In-Depth Chemistry in Plasma-Exposed M30 and JA2 Gun Propellants

by Rose A. Pesce-Rodriguez, Richard A. Beyer,  
Amy E. Kinkennon, Miguel Del Güercio,  
Pamela J. Kaste, and Joyce E. Newberry

ARL-TR-2505

June 2001

Approved for public release; distribution is unlimited.

20011005 106

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

# Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

---

---

ARL-TR-2505

June 2001

---

## In-Depth Chemistry in Plasma-Exposed M30 and JA2 Gun Propellants

Rose A. Pesce-Rodriguez, Richard A. Beyer,  
Miguel Del Güercio, Pamela J. Kaste, and  
Joyce E. Newberry  
Weapons and Materials Research Directorate, ARL

Amy E. Kinkennon  
National Research Council

---

---

Approved for public release; distribution is unlimited.

---

---

## Abstract

---

JA2 and M30 recovered from interrupted ETC-closed bomb, interrupted ETC small-scale chamber, and open-air experiments were subjected to chemical and microscopic analysis. Evidence of subsurface reaction in both M30 and JA2 has been discovered using a desorption-gas chromatography-mass spectroscopy (D-GC-MS) method to detect low levels of NO in the propellant. It appears that for M30, profiles for radiation-induced denitration of nitrate esters are consistent with Beer's law, and that effects occur as deep as 0.5 mm into the exposed surface. Radiation-induced denitration in JA2 has been detected as deep as 0.75 mm from the exposed surface, but profiles are not consistent with Beer's law. It is suspected that denitration at and below the exposed JA2 surface occurs mostly in locations where large graphite particles are found. Rough estimates of graphite particle temperature when exposed to plasma radiation are in excess of those required for denitration to occur. Microscopic examination of plasma-exposed propellant indicates several features (pits, gouges, blisters, wormholes, etc.) that increase the surface area of the propellant and can contribute to an increased burning rate.

---

## Acknowledgments

---

The authors wish to thank Martin Miller and Bob Fifer of the U.S. Army Research Laboratory (ARL) for useful discussions.

INTENTIONALLY LEFT BLANK.

---

## Contents

---

Acknowledgments	iii
List of Figures	vii
1. Background	1
2. Experimental	3
2.1 Plasma Exposure.....	3
2.2 Microscopy.....	3
2.3 Sample Preparation for D-GC-MS Analysis.....	3
2.4 Desorption-Gas Chromatography-Mass Spectroscopy (D-GC-MS) .....	3
3. Results and Discussion	4
3.1 Microscopy.....	4
3.2 P-GC-MS .....	6
4. Conclusions	10
5. Future Work	11
6. References	13
Distribution List	15
Report Documentation Page	17

INTENTIONALLY LEFT BLANK.



---

## List of Figures

---

Figure 1. Typical TIC and SIC for D-GC-MS analysis of JA2. ....	4
Figure 2. SEM photo of M30 grain exposed to plasma ignition source (Kinkennon et al. 2000).....	5
Figure 3. SEM photos of a 7-perf grain of JA2 recovered from an interrupted ETC-closed bomb experiment (35-MPa blowout). ....	5
Figure 4. SEM photos of a 2.5-mm-thick JA2 sheet exposed to a plasma ignition source in an open-air configuration.....	6
Figure 5. NO ratios for M30 propellant grains.....	7
Figure 6. NO ratios for JA2 propellant sheet.....	8
Figure 7. NO ratios for JA2 propellant grains. ....	9
Figure 8. Optical microscope photo of a 2.5-mm-thick sheet of virgin JA2.....	10

INTENTIONALLY LEFT BLANK.

---

## 1. Background

---

There are a number of advantages to using plasma ignition for gun propulsion, including short, reproducible ignition (Katulka and Dyvik 1996), significantly reduced temperature sensitivity (Dyvik and Katulka 1995; Marinos 1995; Perelmutter et al. 1996), and the ability to ignite charges with very high loading density (White et al. 1995). In addition, it has been observed that propellants burned in closed bombs with plasma ignition exhibit mass generation rates that are significantly higher than those observed with conventional ignition (Woodley and Fuller 1996; Del Güercio 1997). To exploit this technology to its maximum, the interactions between plasma and propellant must be clearly understood. Toward this end, the U.S. Army Research Laboratory (ARL) has undertaken the study of these interactions. Several reports on the chemical characterization and morphological characterization of plasma-exposed propellants have appeared over the past few years. In one of the first such studies, Lieb and Gillich (1994) studied morphological changes in JA2 propellant recovered from a 30-mm electrothermal-chemical (ETC) gun. It was reported that exposed surfaces were pitted and showed evidence of both brittle fracture and plastic flow, and that regions of the propellant showed evidence of augmented mass generation as compared to samples exposed to a conventional ignition system. Lieb postulated that mechanisms to explain observed morphological changes include erosive burning, fracture-generated tunneling, and in-depth burning. Blowout pressures were typically larger than those found by Kaste et al. (1998a, 1998b, 1999) and Kinkennon et al. (2000) to be of use for studying plasma effects, i.e., 95 MPa vs. 35 MPa. Kaste et al. (1998b) examined seven different propellant formulations, including a double base (M9), a modified double base (JA2), a LOVA (HELP-1), and nitramine-filled thermoplastic elastomers (TPEs), all recovered from experiments where the propellant was exposed to plasma in an "open air" configuration. In that study, evidence for the denitration of nitrate esters in the M9 and JA2, the hydrolysis of the cellulosic binder in the LOVA, and a reduction in the level of nitramines in the TPEs was found. In a separate experiment involving shielded JA2 samples, FTIR microscopy revealed carbonyl functional groups, again indicating the that denitration of the nitrate esters had occurred when JA2 was unshielded and shielded by aluminum, but not when it was shielded by Mylar (to shield from UV radiation and convective heating). No evidence of plasticizer depletion was observed in the samples recovered from either of these experiments.

Kaste et al. (1998a) reported on the analysis of M30 and JA2 from interrupted closed bomb experiments with plasma and conventional ignition sources. It was found that denitration at the surface of JA2 occurred at blowout pressures of 75 and 100 MPa, but not at 35 MPa, suggesting that the reaction was a result of burning, not of

exposure to plasma. For both plasma and conventional ignition of M30 at blowout pressures of 75 and 100 MPa, IR bands for nitroguanidine (NQ) decreased relative to other bands in M30's IR spectrum. This is consistent with results reported by Schroeder et al. (1994) and indicates that with normal burning, NQ is depleted at a faster rate than is nitrocellulose. No evidence of plasticizer depletion was detected in any of the samples examined.

Kaste et al. (1999) again analyzed M30 samples recovered from interrupted closed bomb experiments, but this time first notched all of the grains in the propellant charge to indicate their position relative to the igniter so that their original position could be identified when recovered after the experiment. By doing so, grain damage relative to the position in the original charge could be determined, including determining where any unrecovered grains were located relative to the igniter. Scanning electron microscopy (SEM) was used to analyze the perforation surface of polyethylene (PE) plasma ignited samples of M30, and indicated that NQ crystals had been stripped from the surface. Very little evidence of chemical modification of the propellant was found. As in previous studies, no evidence of plasticizer depletion was found for either M30 or JA2 by conventional or plasma ignition. Evidence of aldehyde formation (indicating that denitration had occurred) was found for M30 extinguished at up to 80 MPa. As was found for previous plasma and conventional ignition studies, NQ level decreased as regression increased. X-ray fluorescence (XRF) analysis revealed the presence of Fe (from the closed bomb hardware) and Cu (from the plasma igniter) in the perforations of plasma-ignited M30. Fe was not found in the perforations of conventionally ignited M30 (Cu would not be expected).

Kinkennon et al. (2000) made a complete SEM characterization of conventionally and Mylar plasma-ignited M30. Composite SEM photos of the exterior surface, the end surface, and the center perforation surface were reported. For this study, the grains in the charge were labeled with respect to their position relative to the ignition source, as was done by Kaste et al. (1999). The SEM photos of the plasma-ignited samples revealed a significant amount of damage to the grains. The amount and type of damage sustained varied, depending on the location of the grain in the original charge. The study confirmed that plasma ignition results in a large increase in surface area of the propellant grains, but did not confirm that the surface area increase was sufficient to account for previously reported burn rate enhancements for M30 (Del Güercio 1997).

The original intention for the current study was to apply the strategy used in the Kinkennon et al. (2000) study to JA2. It was expected that the most significant results to be obtained were the morphological changes produced in the JA2 due to plasma exposure. While these changes were found and are partially documented here, it was also found that in-depth chemical changes had occurred in the JA2 recovered from interrupted closed bomb experiments. The study was then expanded to include samples recovered from interrupted small-chamber

experiments and open-air experiments (Beyer 2000), and it was found that the in-depth chemistry had occurred in these samples as well. The focus of this report is on the documentation of this in-depth chemistry and the speculation as to its significance with respect to plasma-propellant interactions.

---

## **2. Experimental**

---

### **2.1 Plasma Exposure**

ETC-closed bomb experiments were performed using nickel wire/Mylar capillary plasma, a blowout disk that ruptured at 35 MPa, and a foam-lined collection chamber as described by Kinkennon et al. (2000). Small-scale chamber and open-air experiments were performed using an aluminum wire/polyethylene plasma as described by Beyer (2000).

### **2.2 Microscopy**

SEM was performed with a JEOL Model JSM-820 instrument. Samples were sputtered with gold prior to examination.

### **2.3 Sample Preparation for D-GC-MS Analysis**

Samples were exposed to either conventional or plasma ignition sources as described by Beyer (2000). Plasma exposure was either through the center of the grain for cylindrical samples, or "head on" for sheet samples. The propellant was either sliced by hand using a razor blade (M30) or microtomed (JA2) to give cross-sectional slices with a thickness of approximately 200  $\mu\text{m}$ . The ends of each slice were trimmed to yield a rectangular sample. The width of each rectangle depended on the particular sample. Lengthwise strips were cut from the rectangular slice. Masses of each strip relative to the total mass of the slice were used to estimate the thickness of each strip. In all cases, slices of samples were analyzed starting with the side exposed to the ignition source and proceeding into the bulk of the sample.

### **2.4 Desorption-Gas Chromatography-Mass Spectroscopy (D-GC-MS)**

Analysis of NO levels was performed by means of D-GC-MS. Desorption was achieved via a CDS Model 2000 Pyroprobe (coil type) connected through a heated interface chamber to the splitless injector of a Hewlett Packard GC-FTIR/MS system (Model 5890 GC, Model 5970 MSD, and Model 5965 IRD with narrow band MCT detector). The GC Column used was a J&W Scientific capillary column (0.32 mm  $\times$  25 m; 3-m DB-17HT film). The injector temperature was 200  $^{\circ}\text{C}$ ; the Pyroprobe

interface temperature was 175 °C. The GC oven temperature program was as follows: 50 °C isothermal for 1 min; 50–250 °C at 40 °C/min; and 250 °C isothermal for 4 min. The Pyroprobe was programmed to give a 20-s desorption pulse at 175 °C. Propellant strips were held within the coil of the Pyroprobe by first placing them in a quartz tube containing a small plug of glass wool and then inserting the entire tube into the coil.

NO levels in propellant samples were determined via Hewlett Packard ChemStation software by first extracting the selected ion chromatogram (SIC) for  $m/z = 30$ , the molecular weight of NO, from the total ion chromatogram (TIC). An example of a TIC and SIC is given in Figure 1. Next, a ratio of the heights of the peaks for neat NO (2.5-min peak) and the NO generated when nitroglycerine (NG) and/or diethylene glycol dinitrate (DEGDN) plasticizers are fragmented at the mass spectrometric detector (5.2-min peak) were obtained. Prior to doing this, NG and DEGDN peak areas were examined to determine that they remained constant across the diameter of propellant samples and could serve as an internal standard.




Figure 1. Typical TIC and SIC for D-GC-MS analysis of JA2.

---

### 3. Results and Discussion

---

#### 3.1 Microscopy

Figure 2 shows a composite photo of an entire M30 grain that had been directly exposed to a plasma ignition source in a closed bomb (Kinkennon et al. 2000). The grain has pits, gouges, chasms, and cracks in the surface. The sides of the grains closest to the plasma had the greatest amount of damage, but even surfaces of grains facing the outer wall of the bomb had small pits. The perforations (not shown) contained gouges and abnormally burned regions (wormholes) that extended into the web.




Figure 2. SEM photo of M30 grain exposed to plasma ignition source (Kinkennon et al. 2000).

The SEM photos of JA2 in Figures 3 and 4 show a different kind of response to the plasma. The photos in Figure 3 are from the ETC-closed bomb experiment and show an almost "lacy" texture on the surface closest to the plasma, while the photos in Figure 4 show blisters that form on the surface of JA2 when exposed to the plasma in an open-air configuration. The cross section of the blistered surface, shown in Figure 4(b), reveals a subsurface pocket. A high magnification photo taken downstream of the area that experienced direct exposure to the plasma shows evidence of pitting. These features were not observed in the photos of virgin propellant (not shown).




Figure 3. SEM photos of a 7-perf grain of JA2 recovered from an interrupted ETC-closed bomb experiment (35-MPa blowout). (A) Exterior surface of grain, located directly adjacent to plasma source, and (B) cross-sectioned grain showing three "striped" perforations and a section of web below the exposed surface (bottom of photo).




Figure 4. SEM photos of a 2.5-mm-thick JA2 sheet exposed to a plasma ignition source in an open-air configuration. (A) 12X photo of exposed surface (approximately one-third of the sample has been cut away); (B) 130X photo of cross section of left edge of sample in Figure 4(a); and (C) 150X photo of section of propellant near the top right-hand corner of Figure 4(a).

### 3.2 P-GC-MS

For all samples, regardless of the ignition source used, it was determined that plasticizer concentrations remained constant across the diameter of the sample (data not shown). This is consistent with high-performance liquid chromatography (HPLC) results reported for M30 and JA2 in a previous study (Kaste et al. 1999). It was observed, however, that the levels of NO in the propellant varied with distance from the exposed surface. Because of tailing and overlapping of the chromatographic peak for NO, it was difficult to quantify by integration of the peak. Peak height was therefore used instead for this purpose and was normalized to the plasticizer peak. Results for the "NO ratio" for plasma-exposed M30 and JA2 suggest in-depth reaction leading to the generation of NO. Figure 5 shows profiles






Figure 5. NO ratios for M30 propellant grains. Nominal thickness is 1.55 mm. Filled boxes represent NO level in slice whose thickness is length of the box; ">>>" indicates regression from the surface.

for NO ratios for M30 exposed to conventional and plasma ignition sources. Figures 6 and 7 show the same for JA2 sheet and grains, respectively. In each of the figures, the vertical bars represent the level of NO in a slice whose thickness is the length of the given bar. Repeated "greater-than" signs (">>>>") indicate how far the exposed surface has regressed as a result of the exposure, and in some cases, of subsequent sustained combustion.

The data for M30 in Figure 5 indicates that the level of NO is nearly constant in unexposed material (Plot A). The level for M30 exposed to a conventional ignition source (Plot B) is approximately the same as for unexposed material, except for the first slice, which is significantly lower. This lower value is the result of char at the surface (presumably black powder residue) that contributes to the sample's mass and thickness, but not to its energetic material or NO level. Data for plasma-exposed M30 (shown in Plots C and D) indicate the presence of elevated NO levels at or directly below the exposed surface. The section of the sample used to generate the data in Plot C regressed more than did the section used to generate the data in Plot D, leaving a small amount of residue that does not contribute to its NO content. However, the level in the second slice is nearly twice that of the baseline, unexposed material. The same is true for the first two slices shown in Plot D; little regression occurred in this area. From these plots, it is estimated that NO-level enhancement occurs as deep as 0.5 mm into the surface, and it is concluded that profiles for radiation-induced in-depth chemistry are consistent with Beer's law (i.e., the effect is greatest at the surface and decreases as the distance from the exposed surface increases).

Figure 6 gives the data for JA2 sheet exposed "head-on" to plasma. Plot A is for unexposed JA2 sheet and serves as a baseline for comparison. Plot B gives data obtained from a sample that was approximately 7 mm away from the area of direct exposure. The sample was covered with residue, but to the naked eye was not otherwise different in appearance than unexposed propellant. Examination by SEM (see Figure 4c) indicates that there was some damage to the sample even downstream from the area of direct exposure to plasma. The data for this area suggests an NO-level enhancement at a depth of 1-1.5 mm. Plots C and D are for two different areas of the section that received direct exposure to the plasma and was obviously blistered and somewhat pitted (as the sample shown in Figure 4a). The data for these areas suggest NO-level enhancement at a depth of 0-0.75 mm.




Figure 6. NO ratios for JA2 propellant sheet. Nominal sample thickness is 2.50 mm. Filled boxes represent NO level in slice whose thickness is the length of the box. Unfilled boxes represent slices for which data was not measured; nominal NO level is assumed.

Figure 7 gives data for JA2 grains exposed to both conventional and plasma ignition sources (micrographs not shown). Neither sample shows any evidence of NO-level enhancement. The plasma-exposed sample actually shows a decreased NO level at the exposed surface. As in the case of the conventionally ignited M30, this is likely due to the fact that the surface regressed significantly and left a residue that contributes to mass and thickness of the sample, but not to its NO level.






Figure 8. Optical microscope photo of a 2.5-mm-thick sheet of virgin JA2.

upwelling of propellant. Depending on the degree of in-depth reaction, the upwelling may result in just a blister, or may burst and leave pits and protrusions at the exposed surface. The consequence of this is an increase in surface area, which in turn will result in an increased burning rate. Chemical analysis of M9 propellant, which contains no graphite but is more energetic than JA2, was not performed because the propellant did not survive the plasma-exposure experiment. It is proposed (Beyer 2000) that the M9 decomposes very rapidly when exposed to the plasma and actually “blows to bits” while still in the small-scale chamber. It is possible that this results from in-depth absorption of radiation that in turn results in in-depth decomposition/gasification which results in the failure in mechanical integrity. The fact that the profiles for in-depth radiation effects in nitrate-ester-rich M30 are consistent with Beer’s law, while those for similarly nitrate ester-rich JA2 are not, is proposed to be due to the multiple internal reflections experienced by radiation at the interfaces of NQ and nitrate ester binder (i.e., scattering increases the path length of the photons and therefore its probability of being absorbed).

---

#### 4. Conclusions

---

- A microscopic examination of plasma-exposed M30 and JA2 has been performed. The examination indicates that M30 and JA2 respond very differently to the plasma.

- In spite of the differences in *how* M30 and JA2 are damaged, it is clear that both experience an increase in surface area as a result of plasma exposure, and this surface area increase can contribute to a concomitant increase in burning rate.
  - Some effects of radiation have been elucidated. For JA2, it appears that absorption of radiation by graphite is the dominant phenomenon, while for M30, absorption of scattered radiation appears to be dominant.
  - For both M30 and JA2, radiation effects are limited to top 1 mm. This is likely not true for M9 and graphite-free JA2. RDX-filled TPE (non-nitrate ester) were examined, but results (not reported here) were inconclusive.
- 

## 5. Future Work

---

- Characterize graphite-free, plasma-exposed JA2.
- Modify D-GC-MS method to detect in-depth chemistry in non-nitrate ester propellants.
- Study effect of absorption of UV radiation by propellant ingredients and potential additives.
- Continue to investigate effects for filled/unfilled propellants.
- Continue work to understand why plasma-induced damage in M30 is so irregular and what initiates pitting.

INTENTIONALLY LEFT BLANK.

---

## 6. References

---

- Beyer, R. A. "Small-Scale Experiments in Plasma Propellant Interactions." Proceedings of the 37th Combustion, 25th Airbreathing Propulsion, 19th Propulsion Systems Hazards, 1st Modeling and Simulation JANNAF Subcommittees Joint Meeting, Monterey, CA, 13-17 November 2000.
- Del Güercio, M. "Propellant Burn Rate Modification by Plasma Injection." *Proceedings of the 34th JANNAF Combustion Meeting*, CPIA Pub. 662, vol. I, pp. 35-42, October 1997.
- Dyvik, J. A., and G. Katulka. "ETC Temperature Compensation: Experimental Results of 120-mm Test Firings." *Proceedings of the 32nd JANNAF Combustion Meeting*, CPIA Pub. 631, vol. III, pp. 109-118, October 1995.
- Kappen, K., and U. H. Bauder. "Calculation of Plasma Radiation Transport for Description of Propellant Ignition and Simulation of Interior Ballistics in ETC Guns." Proceedings of the 10th Electromagnetic Launch Technology Symposium, San Francisco, CA, April 2000. To be published in the January 2001 issue of *IEEE Transactions on Magnetics*. (<http://www.emlsymposium.org/emlsymposium/poster.html>)
- Kaste, P., A. Kinkennon, R. Lieb, A. Birk, M. Del Güercio, J. Newberry, M. Schroeder, and R. Pesce-Rodriguez. "Surface Phenomena of Plasma-Treated Propellant Samples." *Proceedings of the 36th JANNAF Combustion Meeting*, CPIA Pub. 691, vol. II, pp. 77-98, October 1999.
- Kaste, P. J., A. E. Kinkennon, R. A. Pesce-Rodriguez, M. A. Del Güercio, D. D. Devynck, A. Birk, S. L. Howard, and M. A. Schroeder. "Chemical Analysis of Extinguished Solid Propellants From an Interrupted Closed Bomb With Plasma Igniter." *Proceedings of the 35th JANNAF Combustion Subcommittee Meeting*, CPIA Pub. 680, vol. II, pp. 278-291, 1998a.
- Kaste, P. J., R. A. Pesce-Rodriguez, M. A. Schroeder, G. L. Katulka, K. J. White, M. G. Leadore, and A. E. Kinkennon. "Chemical Characterization of Plasma-Treated Solid Gun Propellants." ARL-TR-1798, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, September 1998b.
- Katulka, G., and J. A. Dyvik. "Experimental Results of Electrical Plasma Ignition in 120-mm Solid Propellant Tank Gun Firings." *Proceedings of the 33rd JANNAF Combustion Meeting*, CPIA Pub. 653, vol. III, pp. 103-110, November 1996.

- Kinkennon, A. E., A. Birk, M. Del Güercio, P. Kaste, R. Lieb, J. Newberry, R. Pesce-Rodriguez, and M. Schroeder. "SEM Characterization of Extinguished Grains From Plasma-Ignited M30 Charges." *Proceedings of the 29th Propellant Development and Characterization Subcommittee and 18th Safety and Environmental Protection Subcommittee Joint Meeting*, CPIA Pub. 697, pp. 345-364, May 2000.
- Lieb, R. J., and C. J. Gillich. "Morphology of Extinguished Monolithic JA2 Grains Fired in a 30-mm Solid Propellant Electro-thermal Chemical (SPECT) Gun." ARL-TR-606, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, November 1994.
- Marinos, C. "ETC Ignition and Temperature Sensitivity." *Proceedings of the 32nd JANNAF Combustion Meeting*, CPIA Pub. 631, vol. III, pp. 109-119, October 1995.
- Miller, M. S. Personal communication. U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, October 2000.
- Perelmutter, L., M. Sudai, C. Goldenberg, D. Kimhe, Z. Zeevi, S. Arie, M. Melnick, and D. Melnik. "Temperature Compensation by Controlled Ignition Power in SPECT Guns." *Proceedings of the 16th International Symposium on Ballistics*, San Francisco, CA, pp. 145-152, September 1996.
- Schroeder, M. A., R. A. Fifer, M. S. Miller, R. A. Pesce-Rodriguez, C. J. Selawski, and G. Singh. "Condensed-Phase Processes During Solid Propellant Combustion III: Preliminary Depth-Profiling Studies on XM-39, JA2, M9, M30, and HMX2." ARL-TR-346, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, January 1994.
- Schroeder, M. A., and R. A. Pesce-Rodriguez. "Critical Analysis of Literature Data on Chemical Mechanisms of Plasma-Propellant Interactions." *Proceedings of the 37th Combustion, 25th Airbreathing Propulsion, 19th Propulsion Systems Hazards, 1st Modeling and Simulation JANNAF Subcommittees Joint Meeting*, Monterey, CA, 13-17 November 2000.
- Voronov, A., A. Koleczko, H. Haak, T. Weise, and N. Eisenreich. "Energy Criteria for Combustion Control in a Large Caliber Gun." *Proceedings of the 10th Electromagnetic Launch Technology Symposium*, San Francisco, CA, April 2000. To be published in the January 2001 issue of *IEEE Transactions on Magnetics*. (<http://www.emlsymposium.org/emlsymposium/poster.html>).
- White, K. J., W. F. Oberle, A. A. Juhasz, I. C. Stobie, K. Nekula, G. L. Katulka, and S. Dreisen. "Electrothermal-Chemical (ETC) Propulsion With High Loading Density Charges." ARL-TR-845, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, August 1995.
- Woodley, C. R., and S. Fuller. "Apparent Enhanced Burn Rates of Solid Propellants Due to Plasmas." *Proceedings of the 16th International Symposium on Ballistics*, San Francisco, CA, September 1996.
- Worrell, W. J. Personal communication. Alliant Techsystems, October 2000.



<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC OCA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OSD OUSD(A&T)/ODDR&E(R) DR R J TREW 3800 DEFENSE PENTAGON WASHINGTON DC 20301-3800
1	COMMANDING GENERAL US ARMY MATERIEL CMD AMCRDA TF 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
1	DARPA SPECIAL PROJECTS OFFICE J CARLINI 3701 N FAIRFAX DR ARLINGTON VA 22203-1714
1	US MILITARY ACADEMY MATH SCI CTR EXCELLENCE MADN MATH MAJ HUBER THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB AMSRL D DR D SMITH 2800 POWDER MILL RD ADELPHI MD 20783-1197

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AI R 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI IS T 2800 POWDER MILL RD ADELPHI MD 20783-1197
	<u>ABERDEEN PROVING GROUND</u>
2	DIR USARL AMSRL CI LP (BLDG 305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	PENN STATE UNIVERSITY DEPT OF MECH ENGINEERING S T THYNELL T LITZINGER 309 REBER BUILDING UNIVERSITY PARK PA 16802
1	NORTH CAROLINA STATE UNIVERSITY PROFESSOR OF NUCLEAR ENGINEERING M BOURHAM RALEIGH NC 27695-7909
3	COMMANDER ARDEC AMSTA AR WEE D S DOWNS R FIELD L E HARRIS PICATINNY ARSENAL NJ 07806
	<u>ABERDEEN PROVING GROUND</u>
28	DIR USARL AMSRL WM B W OBERLE AMSRL WM BC P PLOSTINS M DEL GUERCIO AMSRL WM BD W R ANDERSON R A BEYER A BIRK L M CHANG T P COFFEE J COLBURN R A FIFER B E FORCH B E HOMAN P J KASTE C LEVERITT M MCQUAID M S MILLER T C MINOR J A NEWBERRY M J NUSCA R A PESCE-RODRIGUEZ (5 CPS) E SAGAN M SCHROEDER AMSRL WM TB R FREY P BAKER

# REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE June 2001	3. REPORT TYPE AND DATES COVERED Final, August - November 2000	
4. TITLE AND SUBTITLE In-Depth Chemistry in Plasma-Exposed M30 and JA2 Gun Propellants			5. FUNDING NUMBERS 611102.H43	
6. AUTHOR(S) Rose A. Pesce-Rodriguez, Richard A. Beyer, Amy E. Kinkennon,* Miguel Del Güercio, Pamela J. Kaste, and Joyce E. Newberry				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-BD Aberdeen Proving Ground, MD 21005-5066			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-2505	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES *National Research Council (mailing address: U.S. Army Research Laboratory, ATTN: AMSRL-WM-BD, Aberdeen Proving Ground, MD 21005-5066)				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) JA2 and M30 recovered from interrupted ETC-closed bomb, interrupted ETC small-scale chamber, and open-air experiments were subjected to chemical and microscopic analysis. Evidence of subsurface reaction in both M30 and JA2 has been discovered using a desorption-gas chromatography-mass spectroscopy (D-GC-MS) method to detect low levels of NO in the propellant. It appears that for M30, profiles for radiation-induced denitration of nitrate esters are consistent with Beer's law, and that effects occur as deep as 0.5 mm into the exposed surface. Radiation-induced denitration in JA2 has been detected as deep as 0.75 mm from the exposed surface, but profiles are not consistent with Beer's law. It is suspected that denitration at and below the exposed JA2 surface occurs mostly in locations where large graphite particles are found. Rough estimates of graphite particle temperature when exposed to plasma radiation are in excess of those required for denitration to occur. Microscopic examination of plasma-exposed propellant indicates several features (pits, gouges, blisters, wormholes, etc.) that increase the surface area of the propellant and can contribute to an increased burning rate.				
14. SUBJECT TERMS plasma-propellant interactions, ETC, electrothermal chemical, M30, JA2, D-GC-MS, plasma, radiation effects, in-depth chemistry			15. NUMBER OF PAGES 21	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

## USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-2505 (Pesce-Rodriguez) Date of Report June 2001

2. Date Report Received \_\_\_\_\_

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) \_\_\_\_\_

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) \_\_\_\_\_

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. \_\_\_\_\_

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) \_\_\_\_\_

CURRENT  
ADDRESS

\_\_\_\_\_  
Organization

\_\_\_\_\_  
Name

\_\_\_\_\_  
E-mail Name

\_\_\_\_\_  
Street or P.O. Box No.

\_\_\_\_\_  
City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD  
ADDRESS

\_\_\_\_\_  
Organization

\_\_\_\_\_  
Name

\_\_\_\_\_  
Street or P.O. Box No.

\_\_\_\_\_  
City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)  
(DO NOT STAPLE)

---

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

**BUSINESS REPLY MAIL**

FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

DIRECTOR  
US ARMY RESEARCH LABORATORY  
ATTN AMSRL WM BD  
ABERDEEN PROVING GROUND MD 21005-5066



NO POSTAGE  
NECESSARY  
IF MAILED  
IN THE  
UNITED STATES

